



UNITED STATES PATENT AND TRADEMARK OFFICE

I, Andrew Harvey David SUMPTER BSc,  
translator to RWS Group Ltd, of Europa House, Marsham Way, Gerrards Cross,  
Buckinghamshire, England declare;

1. That I am a citizen of the United Kingdom of Great Britain and Northern Ireland.
2. That I am well acquainted with the German and English languages.
3. That the attached is, to the best of my knowledge and belief, a true translation into the English language of the accompanying copy of the specification filed with the application for a patent in Germany on 26 March 2003 under the number 103 13 652.5 and the official certificate attached hereto.
4. That I believe that all statements made herein of my own knowledge are true and that all statements made on information and belief are true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the patent application in the United States of America or any patent issuing thereon.

A handwritten signature in black ink, appearing to read "A. Sumpter", written over a horizontal line.

For and on behalf of RWS Group Ltd

The 21st day of June 2006

**FEDERAL REPUBLIC OF GERMANY**

**[Eagle crest]**

**Priority Certificate  
for the filing of a Patent Application**

**File Reference:** 103 13 652.5

**Filing date:** 26 March 2003

**Applicant/Proprietor:** tesa AG, Hamburg/DE

**Title:** Adhesive

**IPC:** C 09 J, C 08 K

**The attached documents are a correct and accurate reproduction of the original submission for this Application.**

Munich, 13 November 2003

**German Patent and Trademark Office**

**The President**

[Seal of the German Patent  
and Trademark Office]

pp

[signature]

Hoiß

**tesa Aktiengesellschaft**  
**Hamburg**

**Description**

**Adhesive**

10 The invention relates to an adhesive for an adhesive tape which is used in the papermaking or paper-converting industry for flying roll changeover (flying splice) on, for example, coating machines or printing machines where temperature is applied.

15 In the papermaking or paper-converting industry a variety of adhesive tapes are known for flying splice. A particular feature of these adhesive tapes is the high tack, which is needed in order to ensure secure adhesive anchorage during roll changeover at high speeds.

20 Furthermore, high-shear-strength adhesive tapes are used for splice applications where the splice is exposed to elevated temperatures, as for example in calenders or in printing machines with a drying unit.

25 Where adhesive tapes for flying splice are exposed to elevated temperatures, there is a risk of the splice opening in application, since the adhesive suffers cohesive failure at the high temperature.

30 Where, on the other hand, adhesive tapes for high-temperature applications are used in a flying splice, there is a risk of the outgoing paper web not obtaining sufficient contact with the adhesive tape, with the consequence of failure during roll changeover.

Within the prior art there are a number of possibilities for solving this problem, and these are elucidated below. All of the solutions, however, harbour weaknesses through an increase in splicing costs and/or reduction in splicing efficiency.

5 On the one hand it is possible to raise the area of the adhesive bond by means of complex splice pattern geometries. Increasing the area of the adhesive bond is intended to improve the splice security in the thermal zone and/or to modify the contact area in such a way that even adhesive tapes of relatively low tack produce contact with the paper web.

10 On the other hand it is possible to reduce the speed during the actual splicing operation, thereby increasing the contact time and so making the splicing operation more secure.

15 Both processes, however, increase the costs or reduce the splicing efficiency and/or harbour the risk of tearing.

The adhesives used can be divided into repulpable adhesives (A) of high tack and repulpable adhesives (B) of high shear strength.

20 (A) As repulpable adhesives of high tack for flying splice it is possible to use acrylate self-adhesive compositions, which comprise a polymer of 30 to 60% acrylic acid, 30 to 60% butyl acrylate, 0 to 40% ethylhexyl acrylate and 0 to 10% of a vinyl monomer and also, as a plasticizer addition, ethoxylated alkylamines.

25 The ethoxylated alkylamines are preferably ethoxylated C<sub>16</sub>-C<sub>18</sub> alkylamines, which with further preference have from 2 to 25 ethoxy units.

30 The mixing proportion between plasticizer and polymer is from 55 to 75% by weight of plasticizer and from 25 to 45% by weight of polymer. The polymerization takes place free-radically in polar solvents. Partial crosslinking is accomplished with from 0.3 to 0.75% by weight of aluminium chelate, based on the total amount.

(B) As a repulpable adhesive of high shear strength for high temperature loads it is possible to use acrylate self-adhesive compositions, which comprise a polymer of 50 to 90% by weight acrylic acid, 10 to 50% by weight butyl acrylate and 0 to 10% of a vinyl monomer or of 50 to 90% by weight acrylic acid, 30 to 5% by weight butyl acrylate, 30 to 5% by weight ethylhexyl acrylate and 0 to 10% by weight of a vinyl monomer and also a plasticizer addition. As a plasticizer addition use is made of ethoxylated alkylamines, preferably ethoxylated C<sub>16</sub>-C<sub>18</sub> alkylamines, which with further preference have from 2 to 25 ethoxy units.

- 10 The mixing proportion of plasticizer and polymer is from 55 to 75% by weight of plasticizer and from 25 to 45% by weight of polymer.

The polymerization takes place free-radically in polar solvents. Partial crosslinking is accomplished with from 0.5 to 1.5% by weight of aluminium chelate, based on the total amount.

For the high-shear-strength compositions the fraction of the short-chain monomers, such as acrylic acid, for example, in the total polymer is raised and the fraction of the longer-chain esters is reduced. One consequence of this, however, is that these self-adhesive compositions exhibit significantly less tack.

The invention is based on the object of specifying an adhesive having high shear strength and high tack.

- 25 This object is achieved by the features of Claim 1. Judicious embodiments of the invention are apparent from the features of Claims 2 to 5.

Provided in accordance with the invention is an adhesive comprising

- 30 (a) 25 to 45% by weight of a polymer composed of

(a1) from 30 to 60% by weight of acrylic acid, from 30 to 60% by weight of butyl acrylate, from 0 to 40% by weight of ethylhexyl acrylate and from 0 to 10% by weight of a vinyl monomer; or

5 (a2) from 50 to 90% by weight of acrylic acid, from 10 to 50% by weight of butyl acrylate and from 0 to 10% by weight of a vinyl monomer; or

(a3) from 50 to 90% by weight of acrylic acid, from 30 to 5% by weight of butyl acrylate, from 30 to 5% by weight of ethylhexyl acrylate and from 0 to 10% by  
10 weight of a vinyl monomer;

(b) from 55 to 75% by weight of an ethoxylated C<sub>20</sub> alkylamine plasticizer and

(c) from 0.5 to 1.5% by weight of a crosslinker.

15

Surprisingly it has been found that an adhesive of this kind exhibits significantly increased shear strengths in comparison with an adhesive defined under (B), the tack levels being virtually the same although exhibiting only a small drop. The invention accordingly provides high-shear-strength, high-tack, repulpable  
20 adhesives, thereby rendering the prior art solutions completely or very substantially dispensable. The adhesives of the invention, accordingly, can be used for flying splice where temperature is applied.

25

The polymer is advantageously prepared by free-radical polymerization in polar solvents. The adhesive can be partly crosslinked through addition of a crosslinker, in which case it is preferred to mix in from 0.5 to 1% by weight of crosslinker, based on the total amount of the adhesive. A preferred crosslinker used is aluminium chelate.

30

One preferred adhesive comprises a polymer composed of 43% by weight of acrylic acid, 50% by weight of butyl acrylate and 7% by weight of a vinyl monomer. This polymer is advantageously prepared in a polar solvent by

free-radical polymerization and ethoxylated C<sub>20</sub> alkylamine is added as plasticizer. The mixing proportion between plasticizer and polymer is 67% plasticizer and 33% polymer. Partial crosslinking is accomplished with 1% by weight of aluminium chelate, based on the total amount of the adhesive.

5

This adhesive surprisingly exhibits a significantly increased shear strength in comparison with the adhesives specified under (B), with only a slight drop in the tack levels.

10 Preferred compositions of the adhesive are set out in Table 1.

Table 1

Ex. No.	Polymer (% by wt.)	Plasticizer (% by wt.)	Crosslinker (% by wt.)
1	31	68.2	0.8
2	33	66	1
3	34.5	64.2	0.8
4	35	64.3	1.2

15 The adhesives of Examples 1, 3 and 4 gave high shear strengths with virtually the same tack properties as the adhesives described under (B). The adhesive of Example 1 gave a high shear strength with a very slight drop in the tack level as compared with the adhesives defined under (B).

### Claims

5 1. Adhesive comprising

(a) 25 to 45% by weight of a polymer composed of

10 (a1) from 30 to 60% by weight of acrylic acid, from 30 to 60% by weight of butyl acrylate, from 0 to 40% by weight of ethylhexyl acrylate and from 0 to 10% by weight of a vinyl monomer; or

(a2) from 50 to 90% by weight of acrylic acid, from 10 to 50% by weight of butyl acrylate and from 0 to 10% by weight of a vinyl monomer; or

15 (a3) from 50 to 90% by weight of acrylic acid, from 30 to 5% by weight of butyl acrylate, from 30 to 5% by weight of ethylhexyl acrylate and from 0 to 10% by weight of a vinyl monomer;

20 (b) from 55 to 75% by weight of an ethoxylated C<sub>20</sub> alkylamine plasticizer; and

(c) from 0.5 to 1.5% by weight of a crosslinker.

25 2. Adhesive according to Claim 1, characterized in that the polymer has been free-radically polymerized in a polar solvent.

3. Adhesive according to Claim 1, characterized in that it has been partly crosslinked.

30 4. Adhesive according to Claim 1, characterized in that the crosslinker is aluminium chelate.

5. Adhesive according to Claim 1, comprising

(a) 33% by weight of a polymer composed of 43% by weight of acrylic acid,  
5 50% by weight of butyl acrylate and 7% by weight of a vinyl monomer;

(b) 66% by weight of an ethoxylated C<sub>20</sub> alkylamine plasticizer; and

(c) 1% by weight of aluminium chelate.

**Abstract**

5 The invention relates to an adhesive comprising

(a) 25 to 45% by weight of a polymer composed of

10 (a1) from 30 to 60% by weight of acrylic acid, from 30 to 60% by weight of butyl acrylate, from 0 to 40% by weight of ethylhexyl acrylate and from 0 to 10% by weight of a vinyl monomer; or

(a2) from 50 to 90% by weight of acrylic acid, from 10 to 50% by weight of butyl acrylate and from 0 to 10% by weight of a vinyl monomer; or

15

(a3) from 50 to 90% by weight of acrylic acid, from 30 to 5% by weight of butyl acrylate, from 30 to 5% by weight of ethylhexyl acrylate and from 0 to 10% by weight of a vinyl monomer;

20 (b) from 55 to 75% by weight of an ethoxylated C<sub>20</sub> alkylamine plasticizer and

(c) from 0.5 to 1.5% by weight of a crosslinker.